



Joint - Stock Company
"VALMIERAS STIKLA ŠĶIEDRA"

Technical Data Sheet

S 05

Version Nr. 4

		Glass Fibre Netting for indoor plaster reinforcement	
	Characteristic	SSA - 1768 - S SSA - 1768 - SM	Test method
1.	Size of hole, mm	~ 2.5	Comp. method PP – Q – S 05
2.	Weave	Leno	
3.	Construction of fabric, tex	warp: EC 9 - 34 Z 20, sized warp weft: EC 9 - 68	DIN EN 12654
4.	Thread count per 10 cm	warp: 80 +/- 2 weft: 40 +/- 1	DIN 53853
5.	Width, cm	100 + 1/- 0	DIN EN 1773
6.	Weight, g/m ²	60 - 75	DIN EN 12127
7.	L.O.I., %	15 - 25	DIN ISO 1887
8.	Tensile strength, N/50 mm	warp: > 700 weft: > 800	EN ISO 13934.1
9.	Roll length, nom., m	100	

Packing, Storage, Transporting

Packing:

- netting wound on the core with inside diameter 40 or 50 mm,
- rolls wrapped in the plastic and put in the carton vertically,
- cartons are fastened on the wooden pallets.

Transporting, Storage:

- goods have to be stored and transported in the producer's packing,
- clean and dry storage.

24.08.2005